

AG FOIL EUROPE s.r.o.

Družstevná ulica 7, 922 10 Trebatice, Slovensko T: +421 33/7720541 F: +421 33/7720543 obchod@agfoil.com

www.agfoil.com

|| VAT nr.: SK2020170944 | Bank details: Československá obchodná banka a. s. | IBAN: SK8575000000000211050243 || Invoice address: AG Foil Europe s.r.o., Kopčianska 3756/10, 85101, Bratislava 5, Slovakia || The company is registered in the District Court Bratislava insert 99354/B ||

Resin for Textile, black

|| AGT150 ||

Description:

Thermo transfer ribbon is specially recommended for textile printing, but it can be used also for printing on plastics. This foil is designed for printers with flat heads and near edge as well. RESIN requires high printing energy to provide highest level of resistance against abradability and excellent durability against solvents and chemicals. This type of resin foil printed on textile materials is able to be washed in high temperatures, or cleaned and ironed. AGT150 is suitable for printers with flat heads such as Avery, Novexx, Zebra, Datamax, Intermec, Citizen, Sato and others.

Recommended media:

textile applications satin nylon polyester, polypropylene, plastics

Applications:

textile and clothing industry general purpose labeling retail tag and label applications industrial and outdoor applications pharmaceutical and healthcare applications

Technical specifications:

Ink typeresin for fabricsInk quality2,1 to 2,4 g/m2Supportpolyester filmFilm thickness4,5 micronsColorblack

Printing characteristics:

Material to print on polyamide, polyester, polyester satins print speed up to 4 inch/seg Usage conditions $5 \,^{\circ}\text{C} - 35 \,^{\circ}\text{C}$, 30%-85% relative humidity Storage conditions $5 \,^{\circ}\text{C} - 35 \,^{\circ}\text{C}$, 30%-80% relative humidity

Performance:

Resistant to washing (up to 150° C), Resistant to dry cleaning, stone and chemical washing Resistant to ironing (150° C) and fading, AGT150 pasted the controls according to the OekoTex parameters.

^{*} The information contained herein relates only to the specific material identified. The information is given according to our best knowledge and experience as of the date of this data sheet. No representation, guarantee or warranty, express or implied, is made as to the accuracy, reliability or completeness of this information. The receiver of this information is urgently requested to make his own determination as to the information's suitability and completeness for this particular application.